INFOSHEET

CEPRO®
LEADING IN WELDING SAFETY

ATLAS WELDING BLANKET

Description
Atlas is a fiberglass with a specially formulated grey fire-retardant PU-coating on both sides with aluminium pigments to increase the anti-slip properties and resistance to fraying.

Characteristics
Atlas is recommended for vertical use, for example as a welding and grinding curtain in situations in which high temperatures are reached, or as a welding blanket for situations in which less high temperatures are reached.

Application
The maximum application temperature is 550 °C, shortly up to 600°C.


Conditions for use
- CEPRO recommends the use of multiple layers for maximum protection.
- Always use welding blankets at an angle of at least 15 degrees.
- The temperatures shown are only an indication. The suitability of the selected product should always be tested beforehand.
- Regularly check welding blankets for tears and or other damage. Replace damaged blankets where necessary.
- Welding blankets can be used for many purposes and therefore, no guarantee can be given on their use. The end user is responsible for determining whether the welding blanket is suitable for use in a specific situation and whether it offers sufficient protection during the work to be performed.
- CEPRO welding blankets are sewn on the cut edges with best quality Kevlar thread.

Available dimensions

Atlas welding blanket, 100x100 cm	56.50.11
Atlas welding blanket, 200x100 cm	56.50.12
Atlas welding blanket, 200x200 cm	56.50.15
Atlas welding blanket, 200x300 cm	56.50.16
Atlas welding blanket, 300x300 cm	56.50.17
Atlas welding blanket, 400x300 cm	56.50.18
Atlas welding blanket, 400x400 cm	56.50.19

Part of al roll, width 100 cm	56.50.05.1000
Full roll 25 m[1], width 100 cm	56.50.05.1025
Part of al roll, width 150 cm	56.50.05.1500
Full roll 50 m[1], width 150 cm	56.50.05.1550
Made to size welding blanket	56.50.10





Version 001 - Check our website for the latest version.
CEPRO_PFS_Welding blankets_Basic_Atlas_1EN_rev

ATLAS WELDING BLANKET

CREPIM
Société par Actions Simplifiée -792 178 816 R.C.S. ARRAS
Siege social : Parc de la Porte Nord - rue Christophe Colomb.
62700 BRUAY LA BUISSIERE France
Tél.: 03.21.61.64.00 Fax : 03.21.61.64.01
E-mail : contact@crepim.fr www.crepim.fr
SIRET 792 178 816 00015 / APE 7112B / T.V.A. FR85 792 178 816

Le classement complémentaire en relation avec la production de fumée est / *Complementary classification in relation to smoke production is:* **s1.**

Le classement complémentaire en relation avec les gouttelettes/particules enflammées est / *Complementary classification in relation to fall of flaming droplets/particles is*: **d0.**

Le format du classement de réaction au feu pour les produits de construction, à l'exception des revêtements de sol et des produits d'isolation thermique pour conduites linéaires est / *The format of the reaction to fire classification for construction products excluding flooring and linear pipe thermal insulation products is:*

Comportement au feu *Fire behaviour*		**Production de fumée** *Smoke production*			**Gouttelettes enflammées** *Flaming droplets*	
A2	**-**	**s**	**1**	**,**	**d**	**0**

Autrement dit / *In other words*, A2 – s1, d0

Classement de réaction au feu / *Reaction to fire classification* :	A2-s1,d0

4.3 Champ d'application / *Field of application*:

Le présent classement est valable pour les paramètres suivants liés au produit / *The classification is valid for the following product parameters* :

Composition : Aucune variation autorisée / *No variation allowed*

Epaisseur / *Thickness*: 0.4 – 0.7 mm

Masse surfacique / *Surface density*: 0.46 – 0.72 kg/m²

Face exposée / *Exposed face* : Faces identiques / *Identical faces*

Couleur / *Color* : Gris / *Grey*

Le classement est valable pour les conditions d'utilisation finale suivantes / *The classification is valid for the following end-use condition:*

Support / *Substrate* : Acier 0.8mm 7850kg/m3 et tous les substrats d'utilisation finale classés A1 de densité supérieure à 5887.5 kg/m^3 et dont la température de fusion est supérieur à 1000°C / *Used over a Steel 0.8mm 7850kg/m3 and all substrates classified A1 which density is superior to 5887.5 kg/m^3 and having a fusion temperature superior to 1000°C.*
Fixation / *Mounting method*: Chaque échantillon est fixé mécaniquement et suspendu librement par-dessus un cadre métallique créant une lame d'air de 40mm / *Each sample is mechanically fixed and freely suspended over a metal frame creating a 40mm thick air gap.*

Pour déclarer, ou non, la conformité à la spécification, il n'a pas été tenu explicitement compte de l'incertitude associée au résultat
Whether or not to declare compliance with the specification, the uncertainty associated with the result was not explicitly taken into account
La reproduction de ce rapport d'essai n'est autorisée que sous sa forme intégrale
Reproduction of this test report is only permitted in its full form
Le CREPIM ne peut être tenu responsable des informations relatives à l'élément testé. Ces informations sont fournies par le demandeur.
CREPIM cannot be held responsible for information relating to the tested element. This information is provided by the applicant

ATLAS WELDING BLANKET

1. IDENTIFICATION OF THE SUBSTANCE / PREPARATION AND COMPANY

Product description Glass fibre material

Manufacturer / Supplier

Cepro International BV
Provinciënbaan 16
NL-5121 DL RIJEN
The Netherlands

Tel. no. for information / emergency +31 (0)161 22 64 72
Fax no. for information / emergency +31 (0)161 22 49 73

Date of issue February 2014

2. HAZARD INFORMATION

Classification of the substance or mixture
Classification according to Regulation (EC) No 1272/2008 [CLP]
Not determined
Classification according to Regulation 67/548/EEC or 1999/45/EC
No classification
Label elements The product does not require a hazard warning label in accordance with EC-directives. This product is an article and therefore it does not require labelling according to EC directives/GefStoffV.
Other hazards
Physico-chemical hazards no particular hazards known.
Environmental hazards no particular hazards known.
Other hazards none

3. COMPOSITION / INFORMATION ON INGREDIENTS

Range [%]	Substance
85-100	glass CAS:65997-17-3, EINECS/ELINCS: 266-046-0

Comment on component parts No dangerous components.
Substances of Very High Concern - SVHC: substances are not contained or are below 0,1 %.

4. FIRST AID MEASURES

Description of first aid measures
General information Change soaked clothing.

Inhalation Ensure supply of fresh air. In the event of symptoms refer for medical treatment.

Skin contact When in contact with the skin, clean with soap and water. Consult a doctor if skin irritation persists.

Eye contact In case of contact with eyes rinse thoroughly with plenty of water and seek medical advice.

Ingestion Not applicable

Most important symptoms and effects, both acute and delayed
No information available

Indication of any immediate medical attention and special treatment needed
Treat symptomatically
Forward this sheet to the doctor.

ATLAS WELDING BLANKET

5. FIRE-FIGHTING MEASURES

Suitable extinguishing media
Product itself is non-combustible. Fire extinguishing method of surrounding areas must be considered.

Extinguishing media that must not be used
None.

Special hazards arising from the substance or mixture
Unknown risk of formation of toxic pyrolysis products.

Advice for fire-fighters
not applicable
Fire residues and contaminated fire-fighting water must be disposed of in accordance with the local regulations.

6. ACCIDENTAL RELEASE MEASURES

Personal precautions, protective equipment and emergency procedures
Avoid dust formation. Use breathing apparatus if exposed to dust.

Environmental precautions
Not applicable

Methods and material for containment cleaning up
Dispose of absorbed material in accordance with the regulations. Take up mechanically.

Reference to other sections
See section 8+13

7. HANDLING AND STORAGE

Precautions for safe handling
With mechanical processing however fibers can be set free.
Avoid the formation and depositions of dust.
Provide vacuuming if dust raised.
Dust deposits that cannot be avoided must be taken up regularly.

Wash hands before breaks and after work.
Use barrier skin cream
take off contaminated clothing and wash before reuse.

Conditions for safe storage, including any incompatibilities
No special measures necessary.

Specific end use(s)
See product use. section 12

8. EXPOSURE CONTROL / PERSONAL PROTECTION

Control parameters

Ingredients with occupational exposure limits to be monitored (GB)

Range [%]	Substance
85-100	glass CAS: 65997-17-3, EINECS/ELINCS: 266-046-0 Long-term exposure: TLV-TWA: 1 f/cc (respirable): 5 mg/m^3 (inhalable (ACGHIH

Exposure controls

Additional advice on system design
Ensure adequate ventilation on workstation
To pay attention to dust limit value (ACGHI-2011: 10 mg/m^3 particle inhalable; 3 mg/m^3 particle respirable).

Eye protection
Safety glasses

Hand protection
The details concerned are recommendations. Please contact the glove supplier for further information.
Leather (EN 388).

Skin protection
Long-sleeved work clothes.

CEPRO_PFS_Welding blankets_Basic_Atlas_2EN_rev Version 001 - Check our website for the latest version.

ATLAS WELDING BLANKET

Other Avoid contact with eyes and skin.
Do not inhale dust.
Personal protective equipment should be selected specifically for the working place, depending on concentration and quantity of the hazardous substances handled. The resistance of these equipments to chemicals should be ascertained with the respective supplier.

Respiratory protection: Breathing apparatus in the event of high concentrations.
Short term: filter apparatus, filter P2.

Thermal hazards No information available

Delimitation and monitoring of the environmental exposition:
not determined

9. PHYSICAL AND CHEMICAL PROPERTIES

Form	Solid in different forms.	**Vapour pressure (kPa)**	Not applicable.
Colour	Various.	**Density (g/m)**	Not determinated.
Odour	Odourless.	**Bulk density (kg/m³)**	Not applicable.
pH-value	Not applicable.	**Solubility in water**	Immiscible.
pH-value, 1 %	Not applicable.	**Partition coefficient: n-octanol / water**	Not applicable.
Boiling point (°C)	Not applicable.	**Viscosity**	Not applicable.
Flash point (°C)	Not applicable.	**Relative vapour density determined in air**	Not applicable.
Flammability (°C)	Not applicable.	**Evaporation speed**	Not applicable.
Lower explosion limit	Not applicable.	**Melting point (°C)**	Not determinated.
Upper explosion limit	Not applicable.	**Autoignition temp. (°C)**	Not applicable.
Combustible properties	No.	**Decomposition temp. (°C)**	Not applicable.

Other information No information available

10. STABILITY AND REACTIVITY

Reactivity No hazardous reactions known
Chemical stability Stable under normal ambient conditions (ambient temperature)
Possibility of hazardous reactions
No hazardous reactions known
Conditions to avoid No information available
Incompatible materials No information available
Hazardous decompostions products
No hazardous products known

11. TOXICOLOGICAL INFORMATION

Acute oral toxicity: not determined
Acute dermal toxicity: not determined
Acute inhalational toxicity: not determined
Irritant effect on eye: not determined
Irritant effect on skin: not determined
Sensitization: not determined
Subacute toxicity: not determined
Chronic toxicity: not determined
Mutagenicity: not determined
Reproduction toxicity: not determined
Carcinogenicity: not determined
Experiences made in practice: Contains fibres with diameter > 6 micrometers. The filament is not breathable (WHO).
Fiber abrasion can cause mechanical skin irritation.
General remarks: No classification on the basis of the calculation procedure of the preparation directive.

ATLAS WELDING BLANKET

12. ECOLOGICAL INFORMATION

Toxicity

Persistence and degradability
Behaviour in environment compartments
not applicable
Behaviour in sewage plant not applicable
Biological degradability not applicable

Bioaccumulative potential No information available

Mobility in soil No information available

Results of PBT and vPvB assessment
No information available

Otherwise adverse effects The product is insoluble in water.
Can be separated out mechanically in purifications plants.

13. DISPOSAL CONSIDERATIONS

Waste treatment methods
Waste material must be disposed of in accordance with the Directive on waste 2008/98/EC as well as other national and local regulations. it is not possible to determine a waste code for this product in accordance with the European Wast Catalogue (EWC) since it is only possible to classify it according to how it is used by the customer. The waste code is to be determined within the EU in liaison with the waste-disposal operator.

Product
Coordinate disposal with the authorities if necessary.

Waste no. (recommended) 101112
101103

Contaminated packaging
Uncontaminated packaging may be taken for recycling

Waste no. (recommended) 150101
150102

14. TRANSPORT INFORMATION

UN number see section 14 in accordance with UN shipping name
UN proper shipping name
Transport by land according to ADR/RID NO DANGEROUS GOODS
Inland navigation (ADN) NO DANGEROUS GOODS
Marine transport in accordance with IMDG NO DANGEROUS GOODS
Air transport in accordance with IMDG NO DANGEROUS GOODS

Transport hazard class(es) see section 14 in accordance with UN shipping name
Packing group see section 14 in accordance with UN shipping name
Environmental hazards see section 14 in accordance with UN shipping name
Special precautions for user relevant information under section 6 to 8
Transport in bulk according to Annex II of MARPOL73/78 and the IBC code
not applicable

ATLAS WELDING BLANKET

15. REGULATORY INFORMATION

Safety, health and environmental regulations/legislation specific for the substance or mixture

EEC-REGULATIONS:	1967/548 (2008/58, 30. ATP/ 31. ATP); 1991/689 (2001/118); 1999/13; 2004/42; 648/2004; 1907/2006 (Reach); 1272/2008; 75/324/EWG (2008/47/EG
TRANSPORT-REGULATIONS:	DOT-Classification, ADR (2009); IMDG-Code (34. Amdt.); IATA-DGR (2010).
NATIONAL REGULATIONS (GB)	EH40/2005 Workplace exposure limits with amendments October 2007. CHIP 3/ CHIP 4

Observe employment restrictions for people

Not applicable

OC (1999/13/CE) Not applicable

Chemical safety assessment Chemical safety assessments for substances in this mixture were not carried out

15. OTHER INFORMATION

Abbreviations and acronyms:

ADR = Accord européen relatif au transport international des marchandises Dangereuses par Route
RID = Règlement concernant le transport international ferroviaire de marchandises dangereuses
ADN = Accord européen relatif au transport international des marchandises dangereuses par voie de navigation intérieure
CAS = Chemical Abstracts Service
CLP = Classification, Labelling and Packaging
DMEL = Derived Minimum Effect Level
DNEL = Derived No Effect Level
EC50 = Median effective concentration
ECB = European Chemicals Bureau
EEC = European Economic Community
EINECS = European Inventory of Existing Commercial Chemical Substances
ELINCS = European List of Notified Chemical Substances
GHS = Globally Harmonized System of Classification and Labelling of Chemicals
IATA = International Air Transport Association
IBC-Code = International Code for the Construction and Equipment of Ships carrying Dangerous Chemicals in Bulk
IC50 = Inhibition concentration, 50%
IMDG = International Maritime Code for Dangerous Goods
IUCLID = International Uniform ChemicaL Information Database
LC50 = Lethal concentration, 50%
LD50 = Median lethal dose
MARPOL = International Convention for the Prevention of Marine Pollution from Ships
PBT = Persistent, Bioaccumulative and Toxic substance
PNEC = Predicted No-Effect Concentration
REACH = Registration, Evaluation, Authorisation and Restriction of Chemicals
TLV®/TWA = Threshold limit value – time-weighted average
TLV®STEL = Threshold limit value – short-time exposure limit
VOC = Volatile Organic Compounds
vPvB = very Persistent and very Bioaccumulative

Customs tariff Not determined

Disclaimer: This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

INFOSHEET

CEPRO®
LEADING IN WELDING SAFETY

ATLAS WELDING BLANKET

TECHNICAL DATA

Test			Standard
1. Weave		Atlas 1/7	DIN 61 101 - 1
2. Width		1000 mm	DIN EN 1773
3. Thickness		0,7 mm	DIN EN ISO 2286-3
4. Weight		720 g/m²	DIN 53 854
5. Number of threads	*warp*	16,0 threads/cm	DIN EN 1049 - 2
	weft	15,0 threads/cm	
6. Yarn count	*warp*	204 total	DIN EN ISO 2060
	weft	204 total	
7. Filament diameter	*warp*	9 µm	DIN 53 811
	weft	9 µm	
8. Tensile strength	*warp*	> 5500 N/5 cm	DIN 53 857 - 1
	weft	> 5000 N/5 cm	